



## Main Characteristics

Type of dyeing	Typology	Knot type	Degree of pilling
HAND DYED	CONVENTIONAL	SPLICER	4 (ASTM D3512)

## Colour Fastness

Colour	Dry Rubbing	Wet Rubbing	Washing
Light	4	3.5	3.5
Medium	3.5	3	3
Dark	2.5	2.5	2.5

**Note:** The variation of dry, wet and washed fastness will be  $\pm 0.5$

- For Dry rubbing and Wet rubbing:  
**AATCC Test Method 8**
- For Washing:  
**AATCC Test Method 61 - Option 1A**


## Suggested Colour Card

- Hand Dyed Techniques.
- Custom made colours can be dyed, for this product the reproduction of the colour is influenced by the composition of the yarn.

## Minimum and Increases

- No stock available.
- Minimum order per shade starts at: **40 kg.**
- Minimum production order starts at **320 kg.**
- Smaller orders can be made but subject to surcharges.

## Suggested Label Path



## Certifications



Spun by Michell

## Innovation



## Licences



## Care Instructions

- Hand wash at maximum temperature of 25 °C with neutral soaps and/or softener for natural or fine fibres.
  - Alternatively, dry clean only with the appropriate solvents.
- ✉ For garments with very contrasting colours and/or a striped design, please contact our sales department at: [michell@michell.com.pe](mailto:michell@michell.com.pe)



## Important Notes

- Alpaca contains black hair, which becomes noticeable in **white and light shades.**
  - These should be considered as a characteristic of Alpaca and Alpaca Blended yarns.
  - We use splicers in most of our yarns.
  - The average number of knots per kilo is about 4/5.
  - All our dye stuffs used are heavy metal free, **AZO-Free and comply with the REACH and OEKO-TEX STANDARDS.**
- ✉ For more information, please contact our sales department: [michell@michell.com.pe](mailto:michell@michell.com.pe)

